



NAME: EP548R

Product Description:

"Jampilen EP548R" is a nucleated, antistatic formulated, high fluidity heterophasic copolymer used for thin-walled injection molding. Items made with "Jampilen EP548R" exhibit high stiffness, relatively good impact resistance and excellent antistatic properties. Due to its excellent mold ability and short cycle times, "Jampilen EP548R" allows high productivity rates. The finished items show good mechanical properties, and high dimensional stability.

"Jampilen EP548R" is very well suited for the production of thin-walled articles or articles with long flow paths such as flower pots, containers, housewares, filters, filters housings and appliance components.

"Jampilen EP548R" is suitable for food contact.

Processing Method:

Injection molding

Features:

Good impact strength High stiffness

Typical Applications:

Excellent antistatic properties Excellent mold ability and short cycle times Heterophasic copolymer



Approval:

Thin-walled articles

Articles with long flow paths such as flower pots, containers, housewares, filters, filters housings and appliance components Sports, Leisure and toys, Food

Typical Data(Table):

TYPICAL PROPERTIES	VALUE	UNIT	METHOD
Melt Flow Rate (230 °C, 2.16kg)	21	g/10min	ASTM D1238
Density	0.9	g/cm ³	ASTM D1505
Flexural Modulus	1500	MPa	ASTM D790
Tensile Strength at Yield	27	MPa	ASTM D638
Tensile Elongation at Yield	7	%	ASTM D638
Izod Impact Strength (notched) at 23 °C	85	J/m	ASTM D256
Izod Impact Strength (notched) at -20 °C	50	J/m	ASTM D256
Rockwell Hardness	98	R Scale	ASTM D785
Vicat softening point (10N)	149	°C	ASTM D1525
H.D.T. (0.46 Mpa)	110	°C	ASTM D648
Accelerated oven ageing in air at 150 °C	360	hours	ASTM D3012

This data and information is considered to be correct and offered in good faith as a guide. But we do not warrant or otherwise guarantee the merchantability, fitness for a particular purpose or suitability of this information, products or processes described.