

NAME: Parslen ZH510M

Parslen ZH510M Is a Homopolymer Particularly Suited for the Extrusion of Cast and Water Quenched Blown Film.

Product Description:

Parslen ZH510M exhibits excellent process ability and outstanding optical properties. This makes Parslen ZH510M particularly suitable for packaging food-stuffs such as pasta, snacks, biscuits, bakery products and confectionary. Other applications include film for packaging of flowers, books, stationary, blankets, shirts, and knitwear.

Application:

Parslen ZH510M is also very appropriate for the extrusion of small pipes and drinking straws.

Parslen ZH510M can be used for lamination with polyester, polyamide and aluminum for packaging of snacks, crisps, sweets, coffee, meat products and pre-cooked foods.

In these applications, Parslen ZH510M gives an excellent high gloss finish in laminates and exhibits good printability after Corona treatment.

Parslen ZH510M can also be coextruded with heterophasic copolymer grades to produce high gloss finishes on blow molded pigmented bottles and coextruded sheet.

Values shown are averages and are not to be considered as exact product specifications.

All specimens are prepared by injection molding.

Typical data: (Table)

| Typical Properties [a,b] | Method | Unit | Value(a) | Tolerance |
|---------------------------------------|-------------|-----------|----------|-----------|
| Melt flow rate (230 ° C, 2.16 Kg) | ASTM D 1238 | gr/10 min | 9 | ± 2 |
| Vicat softening point (9.8 N) | ASTM D 1525 | ° C | 155 | ± 4 |
| Н.D.T. (0.46 Мра) | ASTM D 648 | °C | 115 | ± 10 |
| Flexural modulus | ASTM D 790 | MPa | 1500 | ± 150 |
| Tensile strength at yield | ASTM D 638 | MPa | 34 | ± 5 |
| Elongation at yield | ASTM D 638 | % | 13 | - 2 |
| Izod impact strength (notched) at 23° | ASTM D 256 | J/m | 40 | ± 4 |
| Rockwell hardness [R - B Scale] | ASTM D 785 | R- B | 71 | ± 10 |
| Haze | MTM 17031 | % | 1 | ± 0.1 |
| Gloss (45 °C) | MTM 17021 | % | 85 | ± 3 |

www.aydinglobaltrading.com

commercial@aydinglobaltrading.com

+90 552 557 1111
+971 50 466 0357